


WACHUSETT PRECAST, INC.

P.O. Box 901  
72 Pratts Jct. Road  
Sterling, Ma. 01564  
(508) 422-3311  
1-800-244-7544

8' Dia Pit

ORDERING INFORMATION:

- (1) 6' Unit requires 2-3' Sections
- (2) 7' Unit requires 1-3' & 1-4' Section
- (3) 8' Unit requires 2-4' Sections
- (4) 9' Unit requires 3-3' Sections
- (5) 4' Unit requires 1-4' Section



"SPECIFICATIONS & GENERAL NOTES"

- [1] Concrete strength 4,000 PSI @ 28 days. Density 150 PCF.
- [2] Cement, Portland Type I or III. ASTM C150-81.
- [3] Admixtures, air & plasticizers @ ASTM C150-81.
- [4] Reinforcing ASTM A615 for wire fabric, Grade 40 rod.
- [5] Design loading AASHTO HS20-44.